

COVERCOAT^{XL}

Exterior Gloss Level 1 Flat Finish
411901 series



COMPLIANCE INDICATORS



DESCRIPTION

Rodda Paint's CoverCoat XL premium exterior paints are formulated with 100% acrylic resin fortified with X-Link technology specific for all seasons including hot weather, early rain & surfactant resistance. This technology and formula is specific to Rodda Paint, and has been tested in all conditions to ensure the highest quality performance with improved attributes toward fade resistance, dry- to-rain exposure (1-2 hours), Low VOC formula, high build application, including moisture tolerance capability. This technology delivers premium performance, is easy to apply with minimal odor and flows-out to a beautiful uniform finish. The X-Link 100% acrylic resin provides excellent adhesion over most exterior surfaces and remains flexible in the changing temperature conditions of the Northwest. CoverCoat XL finishes exhibit exceptional UV resistance with improved resistance to mold and mildew growth, extending the service life between repaints, and can be applied by brush, roller or airless spray in conditions down to 35°F for early morning starts and extends the painting season with its X-Link Technology early rain and surfactant resistance.

RECOMMENDED USES

CoverCoat XL is available in a flat, velvet, satin, and Low sheen gloss levels for exceptional versatility, and is an excellent choice for new work and repaint projects over properly prepared wood, trim and siding, masonry, brick and concrete, and exterior metal like gutters and downspouts using Rodda Paint's premium PrimeSolutions First Coat primer, Surf Bond II or Control Primer. CoverCoat XL is backed by a Rodda Paint Limited Lifetime Warranty (see your Rodda Sales Rep or Store Manager for details). Available in one gallon cans and five gallon pails, and the CoverCoat XL line is supported by 1320+ colors in Rodda's "Color Right" system, the exclusive Cascadia colors of the Northwest neighborhoods and can be custom-matched to most any color. Vinyl siding should only be repainted with light colors to help avoid warping, see and follow siding manufacturer's recommendations.

TECHNICAL CHARACTERISTICS

Bases	VOC(g/L)*
White Base (411901)	<50.00 g/L (0.38 lbs/gal)
Deep Base (411903)	<50.00 g/L (0.38 lbs/gal)
Neutral Base (411904)	<50.00 g/L (0.38 lbs/gal)

*Before thinning and colorants

TINTING TYPE

Universal Tinting or Zero VOC Colorant

FINISH

Gloss: 2.0 at 60

Sheen: 1.5 to 2.0 at 85

SOLIDS & DENSITY

Volume: 38%

Weight: 51.8 %

Density: 11.06 lb per gallon

FILM THICKNESS (PER COAT)

Wet: 4.0 - mils

THEORETICAL

COVERAGE (PER COAT):

Theoretical coverage is 535 sq. ft. per gallon for 1.0 mil dry

VISCOSITY

98 - 102 KU

DRYING TIME

35-50 (DTR) 1-2 hours

50-77 (DTR) 1-1.5 hours

77-90 (DTR) ½ - 1 hour

Recoat 1-4 hours

THINNER

For roller or brush application thinning is normally not necessary. For spraying purposes thinning up to 10% by volume with clean water is acceptable.

CLEAN UP

After use, clean application tools with warm soapy water and rinse thoroughly.

STORAGE TEMPERATURE

40-90 degrees F. Store indoors and keep from freezing.

SHELF LIFE

2 year minimum-unopened cans at 70 degrees F.

SURFACE PREPARATION

Surface preparation is important. All surfaces must be smooth, clean, dry, free of mildew, grease, chalk, soap film, sanding dust or other contaminants. Remove all loose or peeling material from previously-painted surfaces. Wash with a mild detergent and water solution. Rinse thoroughly, allow to dry. On exterior surfaces after cleaning, check for chalk (paint oxidation) on the surfaces with a dark colored rag. If chalk is still present re-wash affected surfaces. If needed on glossy or smooth surfaces: scuff sand using 80-120 grit sandpaper. Remove all sanding dust prior to painting. Do not apply at ambient temperatures below 35°F (2°C).

New or Bare Wood: Sand or chemically remove mill glaze to expose fresh wood cells prior to applying paint or stain. Woods known to contain soluble stains, such as tannins in cedar and redwood must be primed with Rodda Stain-Blocking primers, such as #501601 or #701501.

Pre-Painted Surfaces: Wash with a mild detergent and water solution. Rinse thoroughly, allow to dry, and then, if needed, scuff sand using 80 to 120 grit sandpaper on a hand sander. Remove all sanding dust.

WARNING! If you scrape, sand or remove old paint from any surface you may release lead dust. LEAD IS TOXIC. EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE, ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE. Wear a NIOSH approved respirator to control lead exposure. Carefully clean up with a wet mop or HEPA vacuum. For additional information on surfaces that may contain lead paint, contact the U.S. EPA / Lead Information Hotline at 1-800-424-LEAD (5323).

APPLICATION

If one is deciding to paint vinyl siding, care must be taken not to use a darker colored paint than the original siding color; as too dark of a color can cause the surface to become very hot in the summer sun and cause warping of the siding.

Do not paint in the direct sun as this can cause lap marks and blistering in your paint job. Always endeavor to paint in the shade.

Application Equipment

Brush: Use a good quality polyester brush

Roller: Use a 3/8" -3/4" nap synthetic cover depending on the degree of texture of the surface to be painted.

Airless Spray: 2,000 p.s.i and a .015" to .019" airless tip

SAFETY PRECAUTIONS

For detailed information please refer to MSDS

Warning

For detailed information please refer to this product's material safety data sheet. A copy of which may be found at our website: www.rodmapaint.com under Products: Product Data Sheets and MSDS.

First Aid: In case of eye contact, flush immediately with plenty of water for at least 15 minutes. Wash contaminated skin with soap and water. If ingested, call physician or the Poison Control Center immediately.

Recent Amendments

Check for recent amendments to this data sheet at www.rodmapaint.com

Last Modification date: 06/28/2017

Limitation of Liability

To the best of our knowledge, the technical data contained herein are true and accurate at the time of issuance but are subject to change without prior notice. We guarantee our product to conform to the specifications contained herein. All technical advice, recommendations and services regarding this product are rendered by the Seller gratis. They are based on technical data which the Seller believes to be reliable and are intended for use by persons having skill and know-how, at their discretion and risk. Seller assumes no responsibility for results obtained or damages incurred from this product use by Buyer whether as recommended herein or otherwise. Such recommendations, technical advice or services are not to be taken as a license to operate under or suggest infringement of any patent.

WARRANTY

Rodda Paint warrants its product to be free from defects in materials and workmanship and will REPLACE ANY PRODUCT PROVED TO BE DEFECTIVE, OR REFUND OF THE ORIGINAL PURCHASE PRICE OF THE QUANTITY PROVED TO BE DEFECTIVE. Requests for refund or replacement of product must be made in writing within one year from the original date of purchase. This Warranty does not apply to defects due, directly or indirectly, to misuse, abuse, negligent application, or acts of God.

Rodda Paint. WILL NOT BE LIABLE FOR DEATH, INJURIES TO PERSONS OR PROPERTY, OR FOR INCIDENTAL, CONTINGENT, SPECIAL OR CONSEQUENTIAL DAMAGES ARISING FROM THE USE OF OUR PRODUCT, INCLUDING DOWNTIME OR LOSS OF USE OF PRODUCT.

All data, statements, and recommendations made herein are based upon information we believe to be reliable, but are made without any representation, guarantee or warranty of accuracy. Our products are sold on the condition that the user himself will evaluate them, as well as our recommendations, to determine their suitability for his own purpose before adoption. Also, statements regarding the use of our products or processes are not to be construed as recommendations for their use in violation of any patent rights or in violation of any applicable laws or regulations.

READ LABEL AND SAFETY DATA SHEET PRIOR TO USE.