

Dryfall

**Acrylic Latex Eggshell Dryfall Coating
533801**



COMPLIANCE INDICATORS

at

DESCRIPTION

Rodda Paint's Dryfall is a professional water-based interior paint formulated for spray application over industrial or commercial ceiling surfaces. Dryfall from Rodda is available in a flat white and flat black, along with a white eggshell finish. The white finishes hide imperfections with best light reflectance values and work well in warehouse ceilings, or areas where little ambient light or fewer light fixtures are present. The flat black finish hides imperfections over a variety of surfaces and allows ceiling structures to be less conspicuous, ideal for public areas and restaurant applications.

RECOMMENDED USES

Rodda's Dryfall is formulated with outstanding adhesion to a wide variety of surfaces to cover solid ceiling structures, vents and ductwork. Under normal environmental conditions, Dryfall has a fall rate of 12-15 feet, allowing overspray to dry before reaching the floor, to be swept for easy clean-up. Dryfall is available in five gallon pails, sprays easily for commercial applications with water clean-up.

FEATURES

- High hiding formulation
- 100% Acrylic Latex formulation for long life durability
- Flash Rust additive to inhibit staining
- Excellent reflectance for increasing light in work areas
- Flat finish to minimize any surface imperfections
- Modified for increased adhesion to clean galvanized substrates
- Excellent resistance to concrete efflorescence
- Great reflectance for increasing light in work area

TECHNICAL CHARACTERISTICS

Bases	VOC(g/L)*
White (533801)	<150 g/L

*Before thinning and colorants

TINTING TYPE

Universal Tinting Colorant

FINISH

Gloss: 20 - 30
Sheen: >65

SOLIDS & DENSITY

Volume: 32.0%
Weight: 43.0%
Density: 9.7 lbs per gallon

FILM THICKNESS (PER COAT)

Wet: 5.0 - mils
Dry: 1.50 - mils

THEORETICAL COVERAGE (PER COAT):

Theoretical coverage of 521 sq ft for 1.0 mil dry film thickness

VISCOSITY

80 - 90 KU

DRYING TIME

at 77°F and 50% Relative Humidity
Dry to touch: 15 minutes
Dry to recoat: 4 hours

THINNER

Do not thin

CLEAN UP

After use, clean application tools with warm soapy water and rinse thoroughly.

STORAGE TEMPERATURE

40-90 degrees F. Store indoors and keep from freezing.

SHELF LIFE

minimum of 2 years when stored unopened in 70 degrees F.

SURFACE PREPARATION

Surface preparation is important. All surfaces must be smooth, clean, dry, free of mildew, grease, soap film, sanding dust or other contaminants. Remove all loose or peeling material from previously-painted surfaces. Wash with a mild detergent and water solution. Rinse thoroughly, allow to dry and if needed on glossy or smooth surfaces: scuff sand using 80-120 grit sandpaper. Remove all sanding dust. Do not apply at ambient temperatures below 50°F (10°C). Allow test patches one week of dry time before testing adhesion to ensure proper cure. Confirm adhesion using ASTM 3359 Method A X-cut Tape Test method with results of 4A to 5A prior to proceeding with application. Contact your Rodda Paint representative with any questions.

Ferrous Metal: Clean metal of any contaminants by pressure washing or solvent wiping per SSPC-SP-1 and SSPC SP3 standards.

Non-Ferrous Metal: Clean the metal surfaces of any contaminants such as chromate pretreatments, oil, grease, or dirt using appropriate methods of abrasion or cleaning. Remove sanding dust before application.

Surface Prep for Unpainted Concrete: Remove all surface contamination, form release agents, moisture curing membranes, mildew, efflorescence, etc. by pressure washing with an appropriate cleaner. Then rinse and allow to dry. Do not apply to damp or wet surfaces. Concrete or mortar needs to be cured approximately 30 days at 70 degrees F. Do not apply block filler to smooth surfaces as peeling may occur.

Wood: Self-priming on properly prepared, clean, and dry new or weathered wood. A natural substrate, some woods known to contain soluble stains, such as tannins in cedar and redwood must be primed with Rodda Stain-Blocking primers, such as #501601.

Pre-Painted Surfaces: Wash with a mild detergent and water solution. Rinse thoroughly, allow to dry, and then, if needed due to a glossy or hard smooth surface: scuff sand using 80 to 120 grit sandpaper on a hand sander. Remove all sanding dust.

APPLICATION

Dry fall coatings may not work properly (fall as dried paint) in damp humid environments.

Application Equipment

Airless Spray: Pressure 2,000 psi. Tip: .017" to .021".

SAFETY PRECAUTIONS

For detailed information please refer to MSDS

Warning

Safety Precautions: For detailed information please refer to this product's material safety data sheet. A copy of which may be found at our website: www.roddapaint.com under Products:Product Data Sheets and MSDS.

First Aid: In case of eye contact, flush immediately with plenty of water for at least 15 minutes. Wash contaminated skin with soap and water. If ingested, call physician or the Poison Control Center immediately.

Recent Amendments

Check for recent amendments to this data sheet at www.roddapaint.com

Last Modification date: 01/16/2017

Limitation of Liability

To the best of our knowledge, the technical data contained herein are true and accurate at the time of issuance but are subject to change without prior notice. We guarantee our product to conform to the specifications contained herein. All technical advice, recommendations and services regarding this product are rendered by the Seller gratis. They are based on technical data which the Seller believes to be reliable and are intended for use by persons having skill and know-how, at their discretion and risk. Seller assumes no responsibility for results obtained or damages incurred from this product use by Buyer whether as recommended herein or otherwise. Such recommendations, technical advice or services are not to be taken as a license to operate under or suggest infringement of any patent.

WARRANTY

Rodda Paint warrants its product to be free from defects in materials and workmanship and will REPLACE ANY PRODUCT PROVED TO BE DEFECTIVE, OR REFUND OF THE ORIGINAL PURCHASE PRICE OF THE QUANTITY PROVED TO BE DEFECTIVE. Requests for refund or replacement of product must be made in writing within one year from the original date of purchase. This Warranty does not apply to defects due, directly or indirectly, to misuse, abuse, negligent application, or acts of God.

Rodda Paint. WILL NOT BE LIABLE FOR DEATH, INJURIES TO PERSONS OR PROPERTY, OR FOR INCIDENTAL, CONTINGENT, SPECIAL OR CONSEQUENTIAL DAMAGES ARISING FROM THE USE OF OUR PRODUCT, INCLUDING DOWNTIME OR LOSS OF USE OF PRODUCT.

All data, statements, and recommendations made herein are based upon information we believe to be reliable, but are made without any representation, guarantee or warranty of accuracy. Our products are sold on the condition that the user himself will evaluate them, as well as our recommendations, to determine their suitability for his own purpose before adoption. Also, statements regarding the use of our products or processes are not to be construed as recommendations for their use in violation of any patent rights or in violation of any applicable laws or regulations.

READ LABEL AND SAFETY DATA SHEET PRIOR TO USE.

