

LEVEL 5 WALL PREP

**Interior Specialty Drywall Primer/Sealer
532516**



COMPLIANCE INDICATORS

at

DESCRIPTION

Level 5 Wall Prep is an interior heavy bodied thixotropic flat vinyl acrylic primer designed to achieve a 'Level 5' Gypsum Board Finish. This Wall Prep eliminates the need for a full Skim Coat of joint compound over the entire gypsum board surface to create a smooth wall finish. When properly applied Level 5 Wall Prep will bring the preparation a gypsum wall or ceiling from 'Level 4' to 'Level 5' as defined in the Dry Wall Finishing Council GA-216 Standard. Formerly labeled Ezee Wall Prep.

RECOMMENDED USES

Level 5 Wall Prep (formerly labeled Ezee Wall Prep) is designed for high production airless spraying of interior wall surfaces. It is to be used as a wallboard and smooth wall preparation to fill in minor defects and even the surface prior to coating to assure a level 5 finish.

FEATURES

- High build nature of Level 5 Wall Prep permits application of 6-10 dry mil without running or sagging to minimize coats needed.

TECHNICAL CHARACTERISTICS

Bases	VOC(g/L)*
White Primer (532516)	<70.0 g/L (0.58 lbs/gal)

**Before thinning and colorants*

TINTING TYPE

Universal Tinting Colorant may be used but this primer was not formulated for tinting so results may vary.

FINISH

Gloss: 0.50 to 1.50

Sheen:

SOLIDS & DENSITY

Volume: 38 %

Weight: 58 %

Density: 12.3 lbs per gallon

FILM THICKNESS (PER COAT)

Wet: 18.0 - 22.0 mils

Dry: 7.0 - 8.5 mils

THEORETICAL COVERAGE (PER COAT):

1 mil dry film thickness is 535 sq ft per gallon

VISCOSITY

105 - KU

DRYING TIME

at 77°F and 50% Relative Humidity

Dry to touch: 1 to 2 hours

Dry to recoat: 2 to 4 hours

THINNER

none recommended

CLEAN UP

After use, clean application tools with warm soapy water and rinse thoroughly.

STORAGE TEMPERATURE

40-90 degrees F. Store indoors and keep from freezing.

SHELF LIFE

minimum two years when stored in unopened containers at 70 degrees F.



TECHNICAL DATA SHEET

SURFACE PREPARATION

Surface preparation is important. All surfaces must be smooth, clean, dry, and free of sanding dust or other contaminants. Remove all loose or peeling material from previously-painted surfaces. Wash with a mild detergent and water solution. Rinse thoroughly, allow to dry. Remove all sanding dust prior to painting. Do not apply at ambient temperatures below 50°F (10°C).

Application Equipment

Airless Spray: Pressure 2,000 psi. Tip: .017" to .021".

SAFETY PRECAUTIONS

For detailed information please refer to MSDS

Warning

Safety Precautions: For detailed information please refer to this product's material safety data sheet. A copy of which may be found at our website: www.rodmapaint.com under Products:Product Data Sheets and MSDS.

First Aid: In case of eye contact, flush immediately with plenty of water for at least 15 minutes. Wash contaminated skin with soap and water. If ingested, call physician or the Poison Control Center immediately.

Recent Amendments

Check for recent amendments to this data sheet at www.rodmapaint.com

Last Modification date: 05/12/2016

Limitation of Liability

To the best of our knowledge, the technical data contained herein are true and accurate at the time of issuance but are subject to change without prior notice. We guarantee our product to conform to the specifications contained herein. All technical advice, recommendations and services regarding this product are rendered by the Seller gratis. They are based on technical data which the Seller believes to be reliable and are intended for use by persons having skill and know-how, at their discretion and risk. Seller assumes no responsibility for results obtained or damages incurred from this product use by Buyer whether as recommended herein or otherwise. Such recommendations, technical advice or services are not to be taken as a license to operate under or suggest infringement of any patent.

WARRANTY

Rodda Paint warrants its product to be free from defects in materials and workmanship and will REPLACE ANY PRODUCT PROVED TO BE DEFECTIVE, OR REFUND OF THE ORIGINAL PURCHASE PRICE OF THE QUANTITY PROVED TO BE DEFECTIVE. Requests for refund or replacement of product must be made in writing within one year from the original date of purchase. This Warranty does not apply to defects due, directly or indirectly, to misuse, abuse, negligent application, or acts of God.

Rodda Paint. WILL NOT BE LIABLE FOR DEATH, INJURIES TO PERSONS OR PROPERTY, OR FOR INCIDENTAL, CONTINGENT, SPECIAL OR CONSEQUENTIAL DAMAGES ARISING FROM THE USE OF OUR PRODUCT, INCLUDING DOWNTIME OR LOSS OF USE OF PRODUCT.

All data, statements, and recommendations made herein are based upon information we believe to be reliable, but are made without any representation, guarantee or warranty of accuracy. Our products are sold on the condition that the user himself will evaluate them, as well as our recommendations, to determine their suitability for his own purpose before adoption. Also, statements regarding the use of our products or processes are not to be construed as recommendations for their use in violation of any patent rights or in violation of any applicable laws or regulations.

READ LABEL AND SAFETY DATA SHEET PRIOR TO USE.



Rodda Paint Company
6107 North Marine Drive, Portland, Oregon, USA 97203
Corporate Office 1.800.452.2315
www.rodmapaint.com



Formulated and Manufactured
in Portland, Oregon, USA

Page 2 of 2
Product: 532516
Printed: 05/11/2017
Version: 05/12/2016